

To be completed and sent to: \_\_\_\_\_



## PROVISIONAL TECHNICAL SPECIFICATION



SUPPLIER	ARTICLE
<b>Name :</b> Aydin Orme Sanayi Ve Ticaret A.S. <b>Address :</b> Saray Mah. Naya Sk, No:3 34768 - Ümraniye ISTANBUL - TURKEY <b>Tel :</b> +90 216 633 2424 <b>Fax :</b> +90 216 633 2431	<b>Supplier Reference :</b> YD 070478 165 195 01 10  <b>Customer's Reference:</b>  <b>Exclusivity :</b> YES / NO

YARN DETAILS			
Material	%		
PA6-UMORFIL	85		
ELASTANE	15		

PROVISIONAL PHYSICAL CHARACTERISTICS			
Parameter	Technical Specification	Sample Test Results	Test Method
Width (cm) :	165 cm $\pm$ 3 ( 160 cm-169 cm )		
Weight (g/m <sup>2</sup> or g/m) :	195 g/m <sup>2</sup> $\pm$ 5% ( 185 g/m <sup>2</sup> - 204 g/m <sup>2</sup> )		
Shrinkage Warp (%) :	$\pm$ 5%		
Shrinkage Weft (%) :	$\pm$ 5%		
Skewness (%) :	max 5%		

Elongation / Modulus	Effective Weight = 3,6 kg	N° of Cycles = 2	
Elongation Warp (%) :		117 $\pm$ % 15	P14 EXTENSION
Elongation Weft (%) :		176 $\pm$ % 15	P14 EXTENSION

Modulus	Measured on 2nd Outgoing Curve	Cycling Load= 3,6 kg	
Warp @ %		185 $\pm$ % 30	P14 EXTENSION
Weft @ %		140 $\pm$ % 30	P14 EXTENSION
Pattern Repeat Length :	-		
Pattern Repeat Width :	-		
pH	4,5-7		

PROVISIONAL COLOR FASTNESS			
TEST	Color Change	Stainig	Test Method
Colour fastness to washing	min 4	min 3/4	ISO 105 C06 B1S
Colour fastness to water	min 4	min 3/4	ISO 105 E01
Colour fastness to perspiration	min 4	min 3/4	ISO 105 E04
Colour fastness to perspiration	min 4	min 3/4	ISO 105 E04
Colour Fastness to Sea Water	min 4	min 3/4	ISO 105 E02
Colour Fast to Chlorinated Water		min 3/4	ISO 105 E03
Colour fast. to rubbing-Wet/dry		min 3/4	ISO 105 X12
Phenolic Yellowing		min 4/5	M&S C20 for White and pale shades
Light fastness	For turquoise 2, neon shades 1/2-other shades $\geq$ 3/4		ISO 105 B02

CARE SYMBOLS									

30°C sensitive washing, don't bleaching, Ironing at low temperature, Dry cleaning

OTHER INFORMATION	
Oeko-Tex	02.T.2346
Process Route	Knitting/Washing/Pre-SettingDyeing/Final Setting/Quality Control
Machine Type	