

To be completed and sent to:



PROVISIONAL TECHNICAL SPECIFICATION



SUPPLIER		ARTICLE
Name :	Aydin Örne Sanayi Ve Ticaret A.S.	Supplier Reference : YD R70494 150 130 R1
Address :	Saray Mah. Naya Sk, No:3 34768 - Ümraniye ISTANBUL - TURKEY	Customer's Reference:
Tel :	+90 216 633 2424	Exclusivity : YES / NO
Fax :	+90 216 633 2431	

YARN DETAILS

Material	%		
RCY PA6	73		
ELASTANE	27		

PROVISIONAL PHYSICAL CHARACTERISTICS

Parameter	Technical Specification	Sample Test Results	Test Method
Width (cm) :	150 cm \pm 3% (145 cm-155 cm)		
Weight (g/m ² or g/m) :	130 g/m ² \pm 5% (123 g/m ² - 136 g/m ²)		
Shrinkage Warp (%) :	\pm 5%		
Shrinkage Weft (%) :	\pm 5%		
Skewness (%) :	max 5%		

Elongation / Modulus Effective Weight = 3,6 kgf N° of Cycles = 2

Elongation Warp (%) :		136 \pm %15	P14 EXTENSION
Elongation Weft (%) :		203 \pm %15	P14 EXTENSION

Modulus Measured on 2nd Outgoing Curve Cycling Load= 3,6 kgf

Warp @ %		193 \pm %30	P14 EXTENSION
Weft @ %		133 \pm %30	P14 EXTENSION
Pattern Repeat Length :	-		
Pattern Repeat Width :	-		
pH	4,5-7		

PROVISIONAL COLOR FASTNESS

TEST	Color Change	Stainig	Test Method
Colour fastness to washing	min 4	min 3/4	ISO 105 C06 B1S
Colour fastness to water	min 4	min 3/4	ISO 105 E01
Colour fastness to perspiration	min 4	min 3/4	ISO 105 E04
Colour fastness to perspiration	min 4	min 3/4	ISO 105 E04
Colour Fastness to Sea Water	min 4	min 3/4	ISO 105 E02
Colour Fast to Chlorinated Water		min 3/4	ISO 105 E03
Colour fast. to rubbing-Wet/dry		min 3/4	ISO 105 X12
Phenolic Yellowing	min 4/5		M&S C20 for White and pale shades
Light fastness	For turquoise 2, neon shades 1/2-other shades \geq 3/4		ISO 105 B02

CARE SYMBOLS



30°C sensitive washing, don't bleaching, Ironing at low temperature, Dry cleaning

OTHER INFORMATION

Oeko-Tex	02.T.2346
Process Route	Knitting/Washing/Pre-SettingDyeing/Final Setting/Quality Control
Machine Type	