To be completed and sent to:

PROVISIONAL TECHNICAL SPECIFICATION

SUPPLIER		ARTICLE	
Name :	**Aydin Örme Sanayi Ve Ticaret A.S.**	Supplier Reference :	**YD 070808 165 170 01**
Address :	**Saray Mah. Naya Sk, No:3**	Customer's Refernce:	
	34768 - Ümraniye		
	ISTANBUL - TURKEY		
Tel :	**+90 216 633 2424**		
Fax :	**+90 216 633 2431**	Exclusivity :	YES / NO

YARN DETAILS				
Material	%			
PA	76			
METALIC	7			
EA	17			

PROVISIONAL PHYSICAL CHARACTERISTICS			
Parameter	Technical Specification	Sample Test Results	Test Method
Width (cm) :	165 ±5% (157 cm - 173 cm)		
Weight (g/m² or g/m) :	170 ±5% (162g/m^2 - 179g/m^2)		
Shrinkage Warp (%) :	±5%		
Shrinkage Weft (%) :	±5%		
Skewness (%) :	max 5%		
Elongation	Effective Weight = 3,6 kgf	N° of Cycles = 2	
Elongation Warp (%) :		125 ±15%	P14 EXTENSION
Elongation Weft (%) :		157 ±15%	P14 EXTENSION
Modulus	Measured on 2nd Outgoing Curve	Cycling Load = 3,6 kgf	
Warp @ %		184 ±30%	P14 EXTENSION
Weft @ %		153 ±30%	P14 EXTENSION
Pattern Repeat Length :	-		
Pattern Repeat Width :	-		
pH	4,5-7		

PROVISIONAL COLOR FASTNESS			
TEST	**Color Change**	**Stainig**	**Test Method**
*CF to Washing	min 4	min 3/4	ISO 105 C06 A1S
*CF to Water	min 4	min 3/4	ISO 105 E01
*CF to Perspiration - Acid	min 4	min 3/4	ISO 105 E04
*CF to Perspiration - Alkaline	min 4	min 3/4	ISO 105 E04
*CF to Sea Water	min 4	min 3/4	ISO 105 E02
*CF to Chlorinated Water @ 20ppm	min 3/4		ISO 105 E03
*CF to rubbing - Wet/Dry	min 3/4		ISO 105 X12
CF to Phenolic Yellowing	min 4/5		ISO105 X18
*CF to Artifical Light	For turqoise 2, neon shades 1/2-other shades ≥3/4		ISO 105 B02

CARE SYMBOLS

30°C sensitive washing, don't bleaching, Ironing at low temperature, Dry cleaning

OTHER INFORMATION	
Oeko-Tex	02.T.2346
Process Route	Knitting/Washing/Pre-SettingDyeing/Final Setting/Quality Control
Machine Type	Circular Knitting

***Colour fastness value is vary depending on the recipe and dye group in which the fabrics is dyed. The valoues written above are standard values. Fastness values specified in lab dip will be valid.**