

To be completed and sent to:



PROVISIONAL TECHNICAL SPECIFICATION



| SUPPLIER | ARTICLE |
|---|--|
| Name : Aydin Örne Sanayi Ve Ticaret A.S. Address : Saray Mah. Naya Sk, No:3 34768 - Ümraniye ISTANBUL - TURKEY Tel : +90 216 633 2424 Fax : +90 216 633 2431 | Supplier Reference : JD 050141 150 170 01 00 Customer's Reference: Exclusivity : YES / NO |

YARN DETAILS

| Material | % | | |
|----------|----|--|--|
| PA | 80 | | |
| EA | 20 | | |

PROVISIONAL PHYSICAL CHARACTERISTICS

| Parameter | Technical Specification | Sample Test Results | Test Method |
|------------------------------------|--|---------------------|-------------|
| Width (cm) : | 150 ±5% (143 cm - 158 cm) | | |
| Weight (g/m ² or g/m) : | 170 ±5% (162 g/m ² - 179 g/m ²) | | |
| Shrinkage Warp (%) : | ±5% | | |
| Shrinkage Weft (%) : | ±5% | | |
| Skewness (%) : | max 5% | | |

| Elongation | Effective Weight = 3,6 kgf | N° of Cycles = 2 | |
|-----------------------|----------------------------|------------------|---------------|
| Elongation Warp (%) : | | 185 ±%15 | P14 EXTENSION |
| Elongation Weft (%) : | | 115 ±%15 | P14 EXTENSION |

| Modulus | Measured on 2nd Outgoing Curve | Cycling Load = 3,6 kgf | |
|-------------------------|--------------------------------|------------------------|---------------|
| Warp @ % | | 145 ±%30 | P14 EXTENSION |
| Weft @ % | | 180 ± %30 | P14 EXTENSION |
| Pattern Repeat Length : | - | | |
| Pattern Repeat Width : | - | | |
| pH | 4,5-7 | | |

PROVISIONAL COLOR FASTNESS

| TEST | Color Change | Stainig | Test Method |
|----------------------------------|--|---------|-----------------|
| *CF to Washing | min 4 | min 3/4 | ISO 105 C06 A1S |
| *CF to Water | min 4 | min 3/4 | ISO 105 E01 |
| *CF to Perspiration - Acid | min 4 | min 3/4 | ISO 105 E04 |
| *CF to Perspiration - Alkaline | min 4 | min 3/4 | ISO 105 E04 |
| *CF to Sea Water | min 4 | min 3/4 | ISO 105 E02 |
| *CF to Chlorinated Water @ 20ppm | min 3/4 | | ISO 105 E03 |
| *CF to rubbing - Wet/Dry | min 3/4 | | ISO 105 X12 |
| CF to Phenolic Yellowing | min 4/5 | | ISO105 X18 |
| *CF to Artificial Light | For turquoise 2, neon shades 1/2-other shades ≥3/4 | | ISO 105 B02 |

CARE SYMBOLS

| | | | | | | | | | |
|--|--|--|--|--|--|--|--|--|--|
| | | | | | | | | | |
|--|--|--|--|--|--|--|--|--|--|

30°C sensitive washing, don't bleaching, Ironing at low temperature, Dry cleaning

OTHER INFORMATION

| | |
|---------------|---|
| Oeko-Tex | 02.T.2346 |
| Process Route | Knitting/Washing/Pre-Setting/Dyeing/Final Setting/Quality Control |
| Machine Type | |

*Colour fastness value is vary depending on the recipe and dye group in which the fabrics is dyed. The valoues written above are standard values. Fastness values specified in lab dip will be valid.