

To be completed and sent to:



PROVISIONAL TECHNICAL SPECIFICATION



SUPPLIER		ARTICLE	
Name :	Aydin Orme Sanayi Ve Ticaret A.S.	Supplier Reference :	JD 030107 150 210 01
Address :	Saray Mah. Naya Sk, No:3 34768 - Ümraniye ISTANBUL - TURKEY	Customer's Reference:	
Tel :	+90 216 633 2424	Exclusivity :	YES / NO
Fax :	+90 216 633 2431		

YARN DETAILS

Material	%		
PA 6	91		
EA	9		

PHYSICAL CHARACTERISTICS

Parameter	Technical Specification	Sample Test Results	Test Method
Width (cm)	150 ±5% (143cm - 158cm)		
Weight (g/m ² or g/m)	210 ±5% (200g/m ² - 221g/m ²)		
Shrinkage Warp (%)	±5%		
Shrinkage Weft (%)	±5%		
Skewness (%)	max 5%		

Elongation		Effective Weight = 3.6 kgf	N° of Cycles = 2
Elongation Warp (%)			132 ±15%
Elongation Weft (%)			39 ±15%
Modulus		Measured on 2nd Outgoing Curve	Cycling Load = 3.6 kgf
Warp @ cN			181 ±30%
Weft @ cN			RIGID
Pattern Repeat Length (cm)		-	
Pattern Repeat Width (cm)		-	
pH		4,5-7	

PROVISIONAL COLOR FASTNESS

TEST	Color Change	Stainig	Test Method
*CF to Washing	min 4	min 3/4	ISO 105 C06 A1S
*CF to Water	min 4	min 3/4	ISO 105 E01
*CF to Perspiration - Acid	min 4	min 3/4	ISO 105 E04
*CF to Perspiration - Alkaline	min 4	min 3/4	ISO 105 E04
*CF to Sea Water	min 4	min 3/4	ISO 105 E02
*CF to Chlorinated Water @ 20ppm		min 3/4	ISO 105 E03
*CF to rubbing - Wet/Dry		min 3/4	ISO 105 X12
CF to Phenolic Yellowing		min 4/5	ISO105 X18
*CF to Artificial Light		For turquoise 2, neon shades 1/2-other shades ≥3/4	ISO 105 B02

CARE SYMBOLS

30°C sensitive washing, Do not bleaching, Ironing at low temperature, Dry cleaning							

OTHER INFORMATION

Oeko-Tex	02.T.2346
Process Route	Knitting/Washing/Pre-SettingDyeing/Final Setting/Quality Control
Machine Type	

*Colour fastness value is vary depending on the recipe and dye group in which the fabrics is dyed. The valoues written above are standard values. Fastness values specified in lab dip will be valid.