

To be completed and sent to: _____



PROVISIONAL TECHNICAL SPECIFICATION



SUPPLIER	
Name :	Aydin Orme Sanayi Ve Ticaret A.S.
Address :	Saray Mah. Naya Sk, No:3 34768 - Ümraniye ISTANBUL - TURKEY
Tel :	+90 216 633 2424
Fax :	+90 216 633 2431

ARTICLE	
Supplier Reference :	JD 010110 160 200 01 00
Customer's Reference:	
Exclusivity :	YES / NO

YARN DETAILS			
Material	%		
PA	85		
EA	15		

PHYSICAL CHARACTERISTICS			
Parameter	Technical Specification	Sample Test Results	Test Method
Width (cm)	160 ±3% (155cm - 165cm)		
Weight (g/m ²)	200 ±5% (190g/m ² -210g/m ²)		
Shrinkage Warp (%)	±5%		
Shrinkage Weft (%)	±5%		
Skewness (%)	max 5%		

Elongation / Modulus		Effective Weight = 3,6 kg	N° of Cycles = 2
Elongation Warp (%)		175 ±15%	P14 EXTENSION
Elongation Weft (%)		95 ±15%	P14 EXTENSION

Modulus		Measured on 2nd Outgoing Curve	Cycling Load = 3,6 kg
Warp @ 40%		125 ±30%	P14 EXTENSION
Weft @ 40%		150 ±30%	P14 EXTENSION
Pattern Repeat Length	-		
Pattern Repeat Width	-		
pH	4,5-7		

PROVISIONAL COLOR FASTNESS			
TEST	Color Change	Stainig	Test Method
*CF to Washing	min 4	min 3/4	ISO 105 C06 A1S
*CF to Water	min 4	min 3/4	ISO 105 E01
*CF to Perspiration - Acid	min 4	min 3/4	ISO 105 E04
*CF to Perspiration - Alkaline	min 4	min 3/4	ISO 105 E04
*CF to Sea Water	min 4	min 3/4	ISO 105 E02
*CF to Chlorinated Water @ 20ppm	min 3/4		ISO 105 E03
*CF to rubbing - Wet/Dry	min 3/4		ISO 105 X12
CF to Phenolic Yellowing	min 4/5		ISO105 X18
*CF to Artificial Light	For turquoise 2, neon shades 1/2-other shades ≥3/4		ISO 105 B02

CARE SYMBOLS							
30°C sensitive washing, don't bleaching, Tumble Dry at low temperature, Ironing at low temperature, Dry cleaning							

OTHER INFORMATION	
Oeko-Tex	02.T.2346
Process Route	Knitting/Washing/Pre-SettingDyeing/Final Setting/Quality Control
Machine Type	HKS 3-M

***Colour fastness value is vary depending on the recipe and dye group in which the fabrics is dyed. The values written above are standard values. Fastness values specified in lab dip will be valid.**