

To be completed and sent to: _____



PROVISIONAL TECHNICAL SPECIFICATION



SUPPLIER		ARTICLE
Name :	Aydin Örne Sanayi Ve Ticaret A.S.	Supplier Reference : YD R70494 150 130 R1
Address :	Saray Mah. Naya Sk, No:3 34768 - Ümraniye ISTANBUL - TURKEY	Customer's Reference:
Tel :	+90 216 633 2424	Exclusivity : YES / NO
Fax :	+90 216 633 2431	

YARN DETAILS			
Material	%		
RECYCLED PA	73		
EA	27		

PROVISIONAL PHYSICAL CHARACTERISTICS			
Parameter	Technical Specification	Sample Test Results	Test Method
Width (cm) :	150 ±5% (143 cm - 158 cm)		
Weight (g/m² or g/m) :	130 ±5%(124 g/m² - 137 g/m²)		
Shrinkage Warp (%) :	±5%		
Shrinkage Weft (%) :	±5%		
Skewness (%) :	max 5%		

Elongation / Modulus		Effective Weight = 3,6 kgf	N° of Cycles = 2
Elongation Warp (%) :		144 ±15%	P14 EXTENSION
Elongation Weft (%) :		210 ±15%	P14 EXTENSION

Modulus		Measured on 2nd Outgoing Curve	Cycling Load = 3,6 kgf
Warp @ %		145 ±30%	P14 EXTENSION
Weft @ %		85 ±30%	P14 EXTENSION
Pattern Repeat Length :	-		
Pattern Repeat Width :	-		
pH	4,5-7		

PROVISIONAL COLOR FASTNESS			
TEST	Color Change	Stainig	Test Method
*CF to Washing	min 4	min 3/4	ISO 105 C06 A1S
*CF to Water	min 4	min 3/4	ISO 105 E01
*CF to Perspiration - Acid	min 4	min 3/4	ISO 105 E04
*CF to Perspiration - Alkaline	min 4	min 3/4	ISO 105 E04
*CF to Sea Water	min 4	min 3/4	ISO 105 E02
*CF to Chlorinated Water @ 20ppm	min 3/4		ISO 105 E03
*CF to rubbing - Wet/Dry	min 3/4		ISO 105 X12
CF to Phenolic Yellowing	min 4/5		ISO105 X18
*CF to Artifical Light	For turquoise 2, neon shades 1/2-other shades ≥3/4		ISO 105 B02

CARE SYMBOLS							

30°C sensitive washing, don't bleaching, Ironing at low temperature, Dry cleaning

OTHER INFORMATION	
Oeko-Tex	02.T.2346
Process Route	Knitting/Washing/Pre-SettingDyeing/Final Setting/Quality Control
Machine Type	Circular Knitting

*Colour fastness value is vary depending on the recipe and dye group in which the fabrics is dyed. The valoues written above are standard values. Fastness values specified in lab dip will be valid.