

To be completed and sent to:



**PROVISIONAL TECHNICAL SPECIFICATION**



SUPPLIER		ARTICLE
Name :	Aydin Örne Sanayi Ve Ticaret A.S.	Supplier Reference : JD 031109 180 120 01
Address :	Saray Mah. Naya Sk, No:3 34768 - Ümraniye ISTANBUL - TURKEY	Customer's Reference:
Tel :	+90 216 633 2424	Exclusivity : YES / NO
Fax :	+90 216 633 2431	

**YARN DETAILS**

Material	%		
PA	66		
EA	34		

**PROVISIONAL PHYSICAL CHARACTERISTICS**

Parameter	Technical Specification	Sample Test Results	Test Method
Width (cm) :	180 ±5% (171 cm - 189 cm)		
Weight (g/m <sup>2</sup> or g/m) :	120 ±5% (114 g/m <sup>2</sup> - 126 g/m <sup>2</sup> )		
Shrinkage Warp (%) :	±5%		
Shrinkage Weft (%) :	±5%		
Skewness (%) :	max 5%		

Elongation	Effective Weight = 3,6 kgf	N° of Cycles = 2	
Elongation Warp (%) :		150 ±%15	P14 EXTENSION
Elongation Weft (%) :		85 ±%15	P14 EXTENSION

Modulus	Measured on 2nd Outgoing Curve	Cycling Load = 3,6 kgf	
Warp @ %		275 ±%30	P14 EXTENSION
Weft @ %		610 ± %30	P14 EXTENSION
Pattern Repeat Length :	-		
Pattern Repeat Width :	-		
pH	4,5-7		

**PROVISIONAL COLOR FASTNESS**

TEST	Color Change	Stainig	Test Method
*CF to Washing	min 4	min 3/4	ISO 105 C06 A1S
*CF to Water	min 4	min 3/4	ISO 105 E01
*CF to Perspiration - Acid	min 4	min 3/4	ISO 105 E04
*CF to Perspiration - Alkaline	min 4	min 3/4	ISO 105 E04
*CF to Sea Water	min 4	min 3/4	ISO 105 E02
*CF to Chlorinated Water @ 20ppm	min 3/4		ISO 105 E03
*CF to rubbing - Wet/Dry	min 3/4		ISO 105 X12
CF to Phenolic Yellowing	min 4/5		ISO105 X18
*CF to Artificial Light	For turquoise 2, neon shades 1/2-other shades ≥3/4		ISO 105 B02

**CARE SYMBOLS**

--	--	--	--	--	--	--	--	--

30°C sensitive washing, don't bleaching, Ironing at low temperature, Dry cleaning

**OTHER INFORMATION**

Oeko-Tex	02.T.2346
Process Route	Knitting/Washing/Pre-SettingDyeing/Final Setting/Quality Control
Machine Type	

\*Colour fastness value is vary depending on the recipe and dye group in which the fabrics is dyed. The valoues written above are standard values. Fastness values specified in lab dip will be valid.